

CR 60 / 80-04-60000

60 ShA / sulfur – ETU crosslinked / black

- Chloroprene rubber (neoprene)
- Polymer, chlorinated butadiene
- Standard material
- Very good resistance to weathering, ageing, ozone, refrigerants, acids and alkalis.
- High resistance to chemical influences, fresh and salt water, wax, fats and non aromatic hydrocarbons.

| Property | Value | Unit | DIN Standard |
|-------------------------------------|------------|-------------------|---------------------|
| Hardness | 60 - 65 | Shore A | DIN ISO 7619-1 |
| Density | 1,44 ±0,03 | g/cm ³ | DIN EN ISO 1183-1 A |
| Tensile strength at 100% elongation | – | N/mm ² | DIN 53504 |
| Elongation at break | ≥ 250 | % | DIN 53504 |
| Tensile strength | ≥ 10 | N/mm ² | DIN 53504 |
| Compression set 70°C/24h | ≤ 25 | % | DIN ISO 815-1 B |
| Rebound resilience | 40 | % | DIN ISO 53512 |
| Tear resistance | 6,0 | N/mm | DIN ISO 34-1 A |
| Tear resistance | 13,3 | N/mm | DIN ISO 34-1 B |
| min. operating temperature | -40 | °C | static |
| min. operating temperature | -35 | °C | constantly |
| max. operating temperature | +100 | °C | constantly |
| max. operating temperature short | +130 | °C | couple of hours |

All above stated data result from random tests which were taken from the ongoing production. All data were established based on standard test-specimen according to ISO, DIN and ASTM standards and can basically not be carried over to the construction element.

Our applied technical advice, either oral, written or through tests is given according to our best knowledge. However, this information is to be considered as non-obligatory instruction, also in terms of any protective rights of a third party, and does not exempt you from testing our product in reference to its suitability for the intended process and purpose. Utilisation, application and processing of the products occur entirely outside of our control and are therefore exclusively your responsibility. However, should a case of liability come into question, it will be limited to all damages in the value of the product which we delivered and you used. By all means, we do warrant the impeccable quality of our products in accordance with our general sales and delivery conditions.